

FKM compounds are widely used in chemical, automotive, aerospace and industrial applications. These compounds offer excellent chemical and temperature resistance. Marco Rubber stocks all USA standard Viton O-Rings sizes, thousands of metric Viton O-Ring and non-standard sizes.

ABOUT #V1003

V1003 is Marco's basic, brown commercial grade compound. It is an FKM Type A. There are many additional specialty compounds based on A, B, F, GLT, GFLT, LTFE and ETP polymer types. Please contact sales@marcorubber.com for assistance in selecting a specialized compound when increased resistance to temperature, chemicals, or physical properties is required.

FEATURES

- High temperature resistance.
- Excellent resistance to acids, fuels, mineral oils, greases, aliphatic, aromatic and chlorinated hydrocarbons, non-flammable hydraulic fluids (HFD) and many organic solvents and chemicals.
- Excellent resistance to aging and ozone.
- Low gas permeability, low compression set.

APPLICATION EXAMPLES

- Vacuum applications
- Acidic applications
- Petroleum applications

ADDITIONAL INFORMATION

- Service Temperature of -15° to 437°F
- Cure System: Bisphenol
- Spec: ASTM 2000 M4HK710 A1-10 B37 EF31 Z1 Z2

This information is accurate and reliable to the best of our knowledge. However, Marco Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It is the customer's responsibility to evaluate parts prior to use.

PHYSICAL PROPERTIES

ORIGINAL PROPERTIES	ASTM D2000	Typical Test Results
Hardness, Shore A, ASTM D2240 (Z1 = 75+/-5)	75 +/- 5	75
Color (Z2 = Brown)	Brown	Brown
Tensile Strength, psi, ASTM D412	1,450min.	1650
Ultimate Elongation, %, ASTM D412	150 Min.	185
HEAT RESISTANCE – A1-10, ASTM D 573 (70 hrs. @ 250°C)	ASTM D2000	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+10 (max)	+5
Tensile Strength Change, %, ASTM D412	-25 (max)	-2
Ultimate Elongation Change, %, ASTM D412	-25 (max)	-16
COMPRESSION SET – B37, ASTM D 395 Method B (22 hrs. @ 200°C)	ASTM D2000	Typical Test Results
Permanent Set %	50 (max)	15
FLUID RESISTANCE – ASTM Fuel C – EF31, ASTM D 471(70 hrs. @ 23°C)	ASTM D2000	Typical Test Results
Hardness Change, Shore A, ASTM D2240	+/- 5	-3
Tensile Strength Change, %, ASTM D412	-25 (max)	-18
Ultimate Elongation Change, %, ASTM D412	-20 (max)	-13
Volume Change, %, ASTM D471	0 to + 10	4